

PRODUCT
SPECIFICATION
产品规格书

Type Designation:	6LR61(9V) Hi-Tech
电池型号:	
Prepared by:	何峰良
编制:	
Checked by:	王世
审核:	
Approved by:	胡陈波
批准:	
Issued Date:	2025-06-18
发布日期:	


PRODUCT SPECIFICATION 产品规格书			
Product 产品	Alkaline Zinc Manganese Dioxide battery; 9.0Volts 碱性锌-二氧化锰电池, 9.0V	Page 页码	1 of 5
Designation 规格	6LR61(9V) Hi-Tech	Document No.	J/PT311156.51-2025(A3)

6LR61(Hi-Tech) battery specification 电池规格书

1.Type designation 电池型号: IEC: 6LR61

JIS: 6LR61

ANSI: 1604A




2.Chemical system 电池化学体系:

Electrolyte-zinc-manganese dioxide (mercury & cadmium free)
碱性电解液-锌-二氧化锰（无汞无镉）

3.Dimension 尺寸: Length 电池长度: 24.5-26.5mm

Width 电池宽度: 15.5-17.5mm

Height 电池高度: 46.5-48.5mm



4.Nominal voltage 标称电压: 9.0Volts

5.Nominal weight 标称重量:

The weight of each battery is approximately 每只电池的重量大约是: **45.5±3g**

6. Reference standard 参考标准:

IEC60086-1:2021——Primary batteries-part 1: General

IEC60086-2:2021——Primary batteries-part 2: Physical and electrical specifications

IEC60086-5:2021——Primary batteries-part 5: Safety of batteries with aqueous electrolyte

ANSI C18.1M,Part 1-2021 Portable primary Cells and Batteries with Aqueous Electrolyte---General and Specifications

ANSI C18.1M,Part 1-2019 Portable primary Cells and Batteries with Aqueous Electrolyte---Safety Standard

7.Heavy Metal content 重金属含量 (%):

Mercury 汞: ≤1ppm; Cadmium 镉: ≤10ppm ; Lead 铅: ≤40ppm

8.Appearance and terminal 电池外观和极端:

Battery shall be clean and have no dirt, no leakage, and no deformation which may affect their performance and actual use and shall have clearly visible markings.

电池外观干净整洁，无脏物、无漏液、无变形以影响电池的性能和实际使用，标志清晰。

PRODUCT SPECIFICATION 产品规格书			
Product 产品	Alkaline Zinc Manganese Dioxide battery; 9.0Volts 碱性锌-二氧化锰电池, 9.0V	Page 页码	2 of 5
Designation 规格	6LR61(9V) Hi-Tech	Document No.	J/PT311156.51-2025(A3)

9.Battery capacity 放电容量: (Test environment 测试环境: 20±2°C, 55+20/-40%RH)

(Load resistance:**620ohms**, Daily period:**24h/d**, Cut off voltage:**4.8V**; According to as the above the same discharge condition, the capacity of each battery is approximately:**700mAh**)

(放电负载: **620Ω**, 放电方式: **24h/d**, 终止电压: **4.8V**; 电池的容量大约是: **700mAh**)

10.Storage characteristics 贮存性能:

After 12 months storage at 20°C±5°C,55+20/-40%RH, 90% capacitance of fresh cells.

20°C±5°C,55+20/-40%RH 条件下贮存 12 个月后, 电池的容量是新电容量的 90%。

After 24 months storage at 20°C±5°C,55+20/-40%RH, 85% capacitance of fresh cells.

20°C±5°C,55+20/-40%RH 条件下贮存 24 个月后, 电池的容量是新电容量的 85%。

11.Electrical characteristics 电气特性:

I		OCV (V) 开路电压	SCC (A)(reference) 短路电流 (参考)
Initial 初始	Normal	9.65	5
	Min	9.5	4
Stored 1 year 储存一年	Normal	9.55	4
	Min	9.4	3

Remark1: OCV: Open Circuit Voltage 开路电压;CCV: closed circuit voltage 闭路电压;

SCC: Short Circuit Current 短路电流.

Remark2: Test environment:20±2°C, 55+20/-40%RH;测试环境: 20±2°C,相对湿度 55+20/-40%

Remark3: All samples shall be normalized for a minimum of 8 hours at the above environment prior to measurement. 测试前, 应在上述环境放置至少 8 小时。

PRODUCT SPECIFICATION 产品规格书			
Product 产品	Alkaline Zinc Manganese Dioxide battery; 9.0Volts 碱性锌-二氧化锰电池, 9.0V	Page 页码	3 of 5
Designation 规格	6LR61(9V) Hi-Tech	Document No.	J/PT311156.51-2025(A3)

12.Discharge test (service life)放电性能:

Applications 应用	Load 负载	Daily Period 放电方式	Cut off Voltage 截止电压	Normal (Initial) 典型值	MAD(Initial) 初始 最小平均值
/	620Ω	24h/d	4.8V	60h	56h
Toy 玩具	270Ω	1h/d	5.4V	24h	22.5h
Clock/Radio 时钟/收音机	620Ω	2h/d	5.4V	56h	52.0h
Smoke detector 烟雾探测器	620Ω(10kΩ)	1s/h,24h/d	7.5V	23.3 days	22.5days

Remark1: Test environment:20±2°C, 55+20/-40%RH

测试环境：20±2°C,相对湿度 55+20/-40%RH

Remark2: A normal value represents the mean derived from long-term repeated testing. MAD value stands for Minimum Average Discharge Time.

Normal 值为长期多次测试的平均值，MAD 值为最小平均放电时间。

Remark3: The initial discharge test shall commence within 60 days of manufacture.

初始放电测试在电池生产后 60 天内进行；

Remark4: Test quantity: n=8pcs (for per discharge test).

检测数量 n=8 节（每一种放电检测）。

PRODUCT SPECIFICATION 产品规格书			
Product 产品	Alkaline Zinc Manganese Dioxide battery; 9.0Volts 碱性锌-二氧化锰电池, 9.0V	Page 页码	4 of 5
Designation 规格	6LR61(9V) Hi-Tech	Document No.	J/PT311156.51-2025(A3)

13.Safety test (Test environment: 20±2°C,55%±20%R.H)

安全测试（测试环境：20±2°C,相对湿度 55%±20%）：

Test item 测试项目	Test method 测试方法	Quantity 数量	Requirements 测试要求
Storage after partial use 部分使用（部分放电）后贮存	See IEC 60086-5 Edition 5.0 6.3.2.1 Test A - Storage after partial use 具体测试方法见 IEC 60086-5（版本 5.0） 6.3.2.1 测试 A-部分使用（部分放电）后贮存	5	No leakage 不泄露 No fire 不着火 No explosion 不爆炸
Transportation-shock 运输-冲击	See IEC 60086-5 Edition 5.0 6.3.2.2 Test B-1 - Transportation-shock 具体测试方法见 IEC 60086-5（版本 5.0） 6.3.2.2 测试 B-1-运输-冲击	5	No leakage 不泄露 No fire 不着火 No explosion 不爆炸
Transportation-vibration 运输-振动	See IEC 60086-5 Edition 5.0 6.3.2.3 Test B-2 - Transportation-vibration 具体测试方法见 IEC 60086-5（版本 5.0） 6.3.2.3 测试 B-2-运输-振动	5	No leakage 不泄露 No fire 不着火 No explosion 不爆炸
Climatic-temperature cycling 气候-温度循环	See IEC 60086-5 Edition 5.0 6.3.2.4 Test C - Climatic-temperature cycling 具体测试方法见 IEC 60086-5（版本 5.0） 6.3.2.4 测试 C-气候-温度循环	5	No fire 不着火 No explosion 不爆炸
External short circuit 外部短路	See IEC 60086-5 Edition 5.0 6.4.2.2 Test E - External short circuit 具体测试方法见 IEC 60086-5（版本 5.0） 6.4.2.2 测试 E-外部短路	5	No fire 不着火 No explosion 不爆炸
Free fall test 自由跌落	See IEC 60086-5 Edition 5.0 6.4.2.4 Test G - Free fall test 具体测试方法见 IEC 60086-5（版本 5.0） 6.4.2.4 测试 G-自由跌落	5	No fire 不着火 No explosion 不爆炸

PRODUCT SPECIFICATION 产品规格书			
Product 产品	Alkaline Zinc Manganese Dioxide battery; 9.0Volts 碱性锌-二氧化锰电池, 9.0V	Page 页码	5 of 5
Designation 规格	6LR61(9V) Hi-Tech	Document No.	J/PT311156.51-2025(A3)

14.Expiry period: 7 years 有效期: 7 年

15.Expiry period marking 有效期表示方法:

14.1 Expiry date marked on the bottom plate of finished battery .

For example:“2032-08” means the expiry date is August 2032.

有效期标在电池的底部: 如 “2032-08” 表示电池的有效期至 2032 年 8 月。

14.2 For private label, can mark according to customer’s requirement.

做 OEM 定牌电池时, 可以根据客户的要求进行标示。

15.Discharge curve 放电曲线:

